



FRICTION MATERIALS

GRADE	Carbon content min (%)	Oxidation resistance	Bulk Density (g/100cc)	Particle size distribution
3I-5-03	94.0	37.70	0.33	+240# : Nil
C-5-03	95.0	64.80	0.31	+200# : Nil
B-1-2	98.0	99.40	0.32-0.33	-100 +200# : 2%
B-1-3	99.0		0.22-0.24	+300 # : Nil +400# : 5% max.
B-1-4	95.0	72.30	0.66	-100# +250
C-0-6	85.0	6.45	0.62	+50# : Nil
A-0-3	96.0		0.33	+200#: 5% max

