



REFRACTORIES

Specially processed from natural graphite having high temperature stability and chemical resistance.

GRADE	Carbon content (% min)	Oxidation resistance	Bulk Density (g/100cc)	Particle size distribution
C-0-7	85.0-90.0	4.91	0.62	+50# : 60%
C-6-02	94.0-95.0		0.32	+200# : Nil
C-12-02	95.0			+52# : 20% max. -52 +80# : 60% min. -80# : 30% max.

